Nourison

Specifications

Sands Point Collection

Style Name	Coastal Plaid
Pile Weight (ASTM D 5848)	56 oz/sq/yd
Total Weight (ASTM D 5848	77 oz/sq/yd
Construction	PP Wilton
Fiber	100% NZ Wool
Pile Height (ASTM D 418)	24"
Total Height (ASTM D 418)	31"
Count and Plies	3Ply, 8.5 count/ 3 Ply
Pitch Width	
Rows Length	
Width	13.2"
Backing	Cotton/ Jute
Pattern repeat Width	39.37"
Pattern repeat Length	38.98"
Flammability (CPSC FF 1-70; 16CFR 1630; ASTM D 2859-96)	
Smoke Density Test (NIST 708; NFPA 258; ASTME 662-97)	
Flooring Radiant Panel Test (ASTME 648-99); FTM 372; NFPA 2:	53)pass
Country of Origin.	China

Product specifications are derived from averages, allowing for normal manufacturing tolerances. As is the case with all textiles, colors are subject to dye lot variations.

Installation should be done only by professional installers with specific expertise with premium broadloom.

Nourison recommends that installations be completed by CFI certified carpet installers with an R2 rating or equivalent.

For conventional tack and pad installations we recommend use of a firm, dense pad.

Fluffing or shedding is a normal occurrence with fine broadloom and natural fibers and does not affect the overall performance of carpet.

Shedding will dissipate with routine vacuuming.

Roll crush is a temporary flattening of carpet pile and can occur with all carpet. Roll crush marks are characterized as a perceived change in the color

Across the width of carpet that appear darker when viewed from one direction and lighter when viewed from the opposite direction.

This is not a manufacturing defect and is usually self correcting by allowing the newly installed carpet to "blossom" as it adjusts to the ambient conditions.

Increasing the relative humidity in the room to 50% or more along with routine vacuuming will expedite pile recovery.

Care and Maintenance:

Proper and routine vacuuming of carpet is the best way to keep carpet clean.

Nourison recommends using a suction only vacuum or a vacuum which allows for the brushes to be turned to the off position.

Overly aggressive agitation of a vacuum can cause damage to all fine carpets and or natural fibers. When spot cleaning carpet always test colorfastness in an inconspicuous area.

Always remove any solids before attempting to clean. For liquid spills gently blot the spot with a clean absorbent white cloth. Do not rub the spot or use a colored towel or cloth as this could result in damage to the area. For cleaning of large areas, rooms or deep cleaning seek a reputable professional carpet cleaning company with specific knowledge of cleaning the specific fiber of your carpet.

For more information contact Nourison or visit nourison.com